



(ESTABLISHED 1932)

116 East 16th Street, New York, N.Y. 10003  
Telephone: 212-777-4410  
TWX: 710-581-6132

August 6, 1984

Advanced Protective Products  
187 Warren Street  
Jersey City, NJ 07302

Att: Mr. Thomas Heiss  
President

DL-6505

OBJECTIVE

To expose steel panels coated with the submitted sample to 300 hours salt fog exposure.

PRODUCT TESTED

RK 1321 Rust Destroyer.

TEST PROCEDURE

The test material was applied to clean cold rolled steel to obtain a dry film thickness of 3 mils. The coating was cured for 7 days at 77°F and exposed to 300 hours salt fog in accordance with ASTM B-117.

TEST RESULTS

After 300 hours exposure there was no sign of rusting or loss of adhesion.

Jerry H. Willner  
Chief Chemist &  
Senior Scientist.

*Saul Spindel*  
Saul Spindel  
President

df